

UHU® ENAMEL REPAIR

WHITE LIQUID FOR REPAIRING DAMAGED ENAMEL AND LACQUER



Points of attention: Contains volatile, highly flammable liquid solvents; appropriate precautions should therefore be taken during storage or during usage. Ensure proper ventilation when used on large areas.

CURE TIMES*

Final bonding strength after: approx. 24 hours

* Curing time may vary depending on a.o. surface, product quantity used, humidity level and ambient temperature.

TECHNICAL SPECIFICATIONS

Appearance: white

Chemical base: synthetic resins

Consistency: Medium viscosity

Solid matter: approx. 46 %

Density: approx. 0,81 g/cm³

STORAGE CONDITIONS

Store in a dry, cool and frost-free place.

PHYSIOLOGICAL PROPERTIES

The dried adhesive is inert, completely neutral and physiologically indifferent.

PRODUCT DESCRIPTION

White repair assistant with brush applicator, suitable for repairing scratches, splinterings, bathtub and sink damage, etc. Resistant to hot water, usual household cleaners and diluted bases.

FIELD OF APPLICATION

For mending scratches, splintering or all kind of damages on white bathtubs and sinks.

PROPERTIES

- White
- Water, temperature and chemical resistant
- Liquid for repairing damaged enamel and lacquer
- Brush in cap
- Discoloring resistant

PREPARATION

Working conditions: Do not use at temperatures below +10°C

Surface requirements: Surfaces which are to be touched up must be clean, dry and free of oil, grease and dust.

Tools: Brush included in bottle cap.

APPLICATION

Directions for use:

Shake bottle before use. Use brush in bottle cap to apply a thin coat of the repair assistant. Let dry, and if necessary, apply a second coat after approx. 10 minutes.

Stains/residue: Remove fresh stains immediately with acetone.

Advice: If necessary, the enamel repair assistant may be diluted with acetone; a colour paste can be used to dye the repair adhesive.

Note: This information is the result of carefully executed tests. This Technical Data Sheet has been prepared to the best of our knowledge to provide you with advice when gluing. We cannot be held responsible for the results or any damage suffered, as the variety of factors involved (type and combination of materials and working method) are beyond our control. Users have to carry out their own checks and trials. Liability can only be accepted for the consistently high quality of our product.