# POLY MAX<sup>®</sup> 10 SEK SOFORT POWER UNIVERSAL CONSTRUCTION ADHESIVE AND SEALANT WITH HIGH INITIAL GRIP AND FAST FINAL STRENGTH BUILD-UP.



### **PRODUCT DESCRIPTION**

Universal assembly adhesive and sealant based on unique SMP technology, with high initial bond strength and fast final strength build-up. For bonding, fixing and sealing almost all (construction) materials on almost all surfaces (both smooth, porous and non-porous surfaces). Very high initial grip. Super fast. Permanently elastic.

# FIELD OF APPLICATION

Bonding: e.g. glass, stone, natural stone, concrete, plasterwork, many synthetic materials, wood, chipboard, Trespa<sup>®</sup>, iron, aluminium, zinc, steel, stainless steel and other metals, ceramic tiles, cork and mirrors.

Fixing: e.g. skirting boards, lathing, window sills, doorsteps, roof edges, construction boards, insulation materials, gypsum boards, polystyrene ornaments and decorative frames.

Sealing: e.g. skirting boards (synthetics), window frames, stair steps, window sills, doorsteps and drywalls. Also suitable for sealing cracks in walls and ceilings. Not suitable for PE, PP, PTFE and bitumen. When gluing plastics always perform an adhesion test first. Adhesion to plastics can vary depending on the type of synthetic and the quality of the plastic.

# PROPERTIES

- · Very high initial bond strength
- · Super-fast building of final bonding strength
- · Very high final bond strength
- $\cdot$  Permanently elastic
- · Can be used internally and externally
- · Paintable (test first)
- · Good filling capacity
- $\cdot$  Resistant to temperatures between -40°C and +100°C
- $\cdot$  UV, water and all-weather resistant
- · 100% adhesive (non-shrinking)
- · Also bonds to slightly damp surfaces
- · Solvent-free
- · Mould resistant
- · Excellent bonding without primer
- · Acid-free, odourless

## PREPARATION

**Working conditions:** Only apply at temperatures between +5°C and +40°C. **Surface requirements:** Both parts must be solid, clean, free of dust and grease. Use of primer not required. The surface may be slightly moist. **Tools:** Apply cartridge contents using a sealant gun (e.g. UHU Power Pistol). If necessary, use a rubber mallet to tap lightly.

#### APPLICATION

**Coverage:** With spot bonding: 5-8 m<sup>2</sup>/kg. Stripes: one cartridge issues approx. 8-15 metres of adhesive (depending on the diameter of the cut nozzle).

# **Directions for use:**

Before using open cartridge at the top by cutting off the plastic nipple above the thread with a sharp knife. Fix the nozzle onto the cartridge and cut at an angle to the desired diameter. Bonding and fixing: Cut the nozzle to a diameter of at least 0.5 cm. Sealing: Cut the nozzle at an angle to the desired joint width. Bonding and fixing: Apply in stripes or dots (every 10 - 40 cm). Always apply to the corners and along the edges of construction boards. Correctly position material within 10 minutes and press firmly or lightly tap with a rubber mallet. If necessary, clamp or fixate heavy materials for 4 hours. Can be handled after 30 minutes (the connection is now strong enough to withstand transportation or a light load); maximum final strength after approx. 4 hours, depending on the surface and the ambient conditions.

Sealing: Evenly apply to the bottom of the joint and tool within 10 minutes using a moistened (with soapy water without lemon) putty knife, sealant smoother, or finger. Tool the vertical joints from bottom to top. Fully cured after a few days (depending on the thickness of the layer). When painting over with alkyd paint, the paint may dry more slowly.

**Stains/residue:** Use white spirit for cleaning tools and removing wet adhesive residue. Dry adhesive residue can only be removed mechanically.

**Points of attention:** The following drying times are based on bonding at least one porous material and an adhesive layer of approx. 1 mm thickness. If two non-porous materials are being bonded and/or the layer of adhesive is thicker, the drying times may be substantially longer.

Note: This information is the result of carefully executed tests. This Technical Data Sheet has been prepared to the best of our knowledge to provide you with advice when gluing. We cannot be held responsible for the results or any damage suffered, as the variety of factors involved (type and combination of materials and working method) are beyond our control. Users have to carry out their own checks and trials. Liability can only be accepted for the consistently high quality of our product.

UHU GmbH & Co. KG 77813 Bühl (Baden) Tel.: (+49) 7223/284-0 Fax (+49) 7223/284-500

64381

20200929

# **UHU POLY MAX® 10 SEK SOFORT POWER** UNIVERSAL CONSTRUCTION ADHESIVE AND SEALANT WITH HIGH INITIAL GRIP AND FAST FINAL STRENGTH BUILD-UP.

#### **CURE TIMES\***

Skinover time: approx. 10-15 minutes Handling time: approx. 30 minutes. This might vary, based on circumstances, like temperature and humidity. Cure rate: approx. 2 mm/24 hrs Drying/Curing time: approx. 4 hours. This might vary, based on circumstances, like temperature and humidity. \* Curing time may vary depending on a.o. surface, product guantity used, humidity level and ambient temperature.

#### **TECHNICAL PROPERTIES**

Moisture resistance: Very good Water resistance: Good Temperature resistance: -40°C - +100°C UV resistance: Good Mildew resistance: Good Chemicals resistance: Good Paintability: Good Filling capacity: Very good

# **TECHNICAL SPECIFICATIONS**

Chemical base: SMP Polymer Colour: White Viscosity: approx. Thixotropic Solid matter: approx. 100 % Density: approx. 1.53 g/cm<sup>3</sup> Tensile strength: approx. 270 N/cm<sup>2</sup> Shear strength: approx. 350 N/cm<sup>2</sup> Flash point: K3 (>55°C) Shrinkage: approx. 0 % Hardness (Shore A): approx. 65 100% modulus: approx. 2.3 MPa Elongation of rupture: approx. 250 %

### **STORAGE CONDITIONS**

At least 18 months after production. Limited shelf life after opening. Close container properly and store in a dry, cool and frost-freeplace.

Note: This information is the result of carefully executed tests. This Technical Data Sheet has been prepared to the best of our knowledge to provide you with advice when gluing. We cannot be held responsible for the results or any damage suffered, as the variety of factors involved (type and combination of materials and working method) are beyond our control. Users have to carry out their own checks and trials. Liability can only be accepted for the consistently high quality of our product.

64381 20200929 2